

Quadrant: E
Section: 7A

6/18/2018

Surface Mix and Materials


Structural Buildup Information

Year of Completion: 2015
Surface Design Method: Superpave
Specified Binder: PG76-22
Surface Mix Stockpiles: Granite/Sand (20% RAP)

Study Layer (in): 1.5
Total HMA (in): 24
Base Material: Granite
Subgrade: Stiff

Research Objective: SBS-Modified 20% RAP Control Mix

Preliminary Field Performance Data for the 2015 Research Cycle



Quadrant: E
Section: 7B

6/18/2018

Surface Mix and Materials

Structural Buildup Information

Year of Completion: 2015
Surface Design Method: Superpave
Specified Binder: PG76-22
Surface Mix Stockpiles: Granite/Sand (25% RAP)

Study Layer (in): 1.5
Total HMA (in): 24
Base Material: Granite
Subgrade: Stiff

Research Objective: SBS-Modified Mix with Higher RAP Content (25%)

Preliminary Field Performance Data for the 2015 Research Cycle

