

Quadrant: E
Section: 9A

6/18/2018

Surface Mix and Materials


Structural Buildup Information

Year of Completion: 2012
Surface Design Method: PFC
Specified Binder: PG76-22
Surface Mix Stockpiles: Granite

Study Layer (in): 0.75
Total HMA (in): 24
Base Material: Granite
Subgrade: Stiff

Research Objective: 9.5 NMAS Mix with Cellulose Fibers

Preliminary Field Performance Data for the 2015 Research Cycle



Quadrant: E
Section: 9B

6/18/2018

Surface Mix and Materials

Structural Buildup Information

Year of Completion: 2012
Surface Design Method: PFC
Specified Binder: PG76-22
Surface Mix Stockpiles: Granite

Study Layer (in): 0.75
Total HMA (in): 24
Base Material: Granite
Subgrade: Stiff

Research Objective: 12.5 NMAS with Forta-Fi and No Cellulose Fibers

Preliminary Field Performance Data for the 2015 Research Cycle

