

Quadrant: N
Section: 1

Surface Mix and Materials

Structural Buildup Information

Year of Completion: 2009
HMA Design Methodology: PFC
Specified Binder: PG76-22
Surface Mix Stockpile Materials: Granite (15% RAP)

Study HMA (in): 0.75
Total HMA (in): 7.75
Base Material: Limerock
Subgrade: Stiff

Research Objective: Surface Cracks in PFC via Spray Paver & M-E Design

Preliminary Field Performance Data

