

Section S2 (Lower Layer)

Laboratory Diary

General Description of Mix and Materials

Design Method:	Superpave
Compactive Effort:	100 gyrations
Binder Performance Grade:	76-22
Modifier Type:	SBS
Aggregate Type:	Gravel
Gradation Type:	BRZ

Avg. Lab Properties of Plant Produced Mix

<u>Sieve Size:</u>	<u>% Passing:</u>
1"	100
3/4"	100
1/2"	86
3/8"	69
No. 4	46
No. 8	30
No. 16	23
No. 30	19
No. 50	11
No. 100	7
No. 200	5.5

Asphalt Binder Content:	4.9%
Compacted Pill Bulk Gravity:	2.282
Theoretical Maximum Gravity:	2.388
Computed Air Voids:	4.4%

Construction Diary

Relevant Conditions for Construction

Completion Date:	Thursday, June 22, 2000
24 Hour High Temperature (F):	92
24 Hour Low Temperature (F):	75
24 Hour Rainfall (in):	0.00
Lift Type:	lower
Design Thickness of Test Mix (in):	2.5

Plant Configuration and Placement Details

<u>Component:</u>	<u>% Setting:</u>
Liquid Binder Setting	4.9%
Gravel 3/4" Crushed Gravel	38.0%
Gravel 3/8" Crushed Gravel	43.0%
Limestone Modified 8910	8.0%
Gravel Coarse Sand	10.0%
Antistrip Hydrated Lime	1.0%

Approximate Length (ft):	200
Surveyed Thickness of Section (in):	NA
Std Dev of Section Thickness (in):	NA
Type of Tack Coat Utilized:	CQS-1h
Target Tack Application Rate:	0.03 gal / sy
Avg Mat Temperature Behind Paver (F):	329
Average Section Compaction:	93.0%

General Notes:

- 1) Mixes are listed chronologically in order of completion date (i.e., construction began with E2 and ended with E1).
- 2) Sections are referenced by quadrant and sequence number, where "E2" refers to section 2 of the east quadrant.
- 3) "dual " lift type indicates that the lower and upper lifts were constructed with the same experimental mix.
- 4) The total thickness of all experimental sections is 4 inches by design, with the exception of S8, S9, S10, S11.
- 5) ARZ, TRZ, and BRZ refer to gradations intended to pass above, through, and below the restricted zone.
- 6) SMA and OGFC refer to stone matrix asphalt and open-graded friction course, respectively.

Section S2 (Upper Layer)

Laboratory Diary

General Description of Mix and Materials

Design Method:	Superpave
Compactive Effort:	100 gyrations
Binder Performance Grade:	76-22
Modifier Type:	SBS
Aggregate Type:	Gravel
Gradation Type:	BRZ

Avg. Lab Properties of Plant Produced Mix

<u>Sieve Size:</u>	<u>% Passing:</u>
1"	100
3/4"	100
1/2"	100
3/8"	96
No. 4	67
No. 8	41
No. 16	29
No. 30	22
No. 50	15
No. 100	10
No. 200	8.4

Asphalt Binder Content:	6.0%
Compacted Pill Bulk Gravity:	2.233
Theoretical Maximum Gravity:	2.342
Computed Air Voids:	4.7%

Construction Diary

Relevant Conditions for Construction

Completion Date:	Tuesday, June 27, 2000
24 Hour High Temperature (F):	92
24 Hour Low Temperature (F):	75
24 Hour Rainfall (in):	0.00
Lift Type:	upper
Design Thickness of Test Mix (in):	4.0

Plant Configuration and Placement Details

<u>Component:</u>	<u>% Setting:</u>
Liquid Binder Setting	6.3%
Gravel 1/2" Crushed Gravel	15.0%
Gravel 3/8" Crushed Gravel	72.0%
AggLime Agricultural Lime	5.0%
Gravel Coarse Sand	7.0%
Antistrip Hydrated Lime	1.0%

Approximate Length (ft):	200
Surveyed Thickness of Section (in):	3.9
Std Dev of Section Thickness (in):	0.0
Type of Tack Coat Utilized:	CQS-1h
Target Tack Application Rate:	0.03 gal / sy
Avg Mat Temperature Behind Paver (F):	325
Average Section Compaction:	93.8%

General Notes:

- 1) Mixes are listed chronologically in order of completion date (i.e., construction began with E2 and ended with E1).
- 2) Sections are referenced by quadrant and sequence number, where "E2" refers to section 2 of the east quadrant.
- 3) "dual " lift type indicates that the lower and upper lifts were constructed with the same experimental mix.
- 4) The total thickness of all experimental sections is 4 inches by design, with the exception of S8, S9, S10, S11.
- 5) ARZ, TRZ, and BRZ refer to gradations intended to pass above, through, and below the restricted zone.
- 6) SMA and OGFC refer to stone matrix asphalt and open-graded friction course, respectively.