

Quadrant: S
Section: 6

Surface Mix and Materials

Structural Buildup Information

Year of Completion: 2009
 HMA Design Methodology: Superpave
 Specified Binder: PG76-22
 Surface Mix Stockpile Materials: Limestone/Porphyry

Study HMA (in): 1.75
 Total HMA (in): 24
 Base Material: Granite
 Subgrade: Stiff

Research Objective: SBS-Modified Superpave Mix

Preliminary Field Performance Data

