

Quadrant: W
Section: 10

6/18/2018

Surface Mix and Materials

Structural Buildup Information

Year of Completion: 2012
Surface Design Method: PFC
Specified Binder: PG76-22
Surface Mix Stockpiles: Traprock (10% RAP)

Study Layer (in): 2
Total HMA (in): 24
Base Material: Granite
Subgrade: Stiff

Research Objective: Conventional PFC

Preliminary Field Performance Data for the 2015 Research Cycle

